

Product name		Product group	Production location
Morvan Waterstruck		S8	Spijk
The most important base material for this type of facing brick is Westerwald clay, a natural white baking clay of the Westerwald region in the western part of Germany. Due to the use of the water-struck-technique the facing bricks sight will appear textured without sand coated surface.			
Colour			
unicoloured anthracite black, textured without sand coated surface (Water-struck)			
Format			
Moulding method		Waterstruck	
WF50mm: 212 x 100 x 53 mm		Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1			
			
EN 771 - CPR-76485 - NOBO 0063 (ex 0620)		EN 771 - 1855-CPR-24911	
2+		2+	
Dimensional tolerances	T2		
Range	R1		
Active Soluble Salts	S2		
Mean Compressive strength	>= 17,5 N/mm <sup>2</sup>	Tested to the bed face	
Normalized Compressive strength	>= 17,5 N/mm <sup>2</sup>	Tested to the bed face	
Dimensional stability	NPD		
Bond Strength general	0,15 N/mm <sup>2</sup>		
Bond Strength thin layer	0,30 N/mm <sup>2</sup>		
Reaction to fire	A1		Category
Water absorption	<= 8% m/md		
Water vapour permeability	50/100		
Net dry density	2100 kg/m <sup>3</sup> (D2)		
Gross dry density	1880 kg/m <sup>3</sup> (D1)		
Thermal conductivity Lambda 50/50	<=0,62 W/m.K		
Durability against freeze thaw	F2		EN 772-22
Dangerous substances	NL-BSB		According to Annex ZA 3
Other Characteristics			
Initial rate of water absorption - Non-coated Bricks	1,5 - 4,0 kg/m <sup>2</sup> .min (IW3)	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1:2011 - 5.3.8	
Freeze/thaw resistance - PTV 23-002	NPD	NBN 27-009	
Thermal conductivity Lambda 90/90	NPD		
Thermal conductivity Lambda Ui	NPD		
Thermal conductivity Lambda Ue	NPD		
			
Storage & handling		Cutting	
<ul style="list-style-type: none"> <li>- Store packs on a clean surface and cover them</li> <li>- Process from multiple packs at the same time</li> <li>- Follow the Vandersanden processing guidelines</li> </ul>		Dry Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	
* All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.			