

| Product name | Product group | Production location |
|------------------|---------------|---------------------|
| Hailsham Mixture | L2 | Lanklaar |

The raw materials are excavated in Weichsel loam layers, the local loam of Aeolian origin dating from the Ice Age. This löss mainly consists of a silt-like fraction, suited ideally for the manufacturing of hand form bricks. By using specific sand types for surface covering, the desired colour is achieved.

| Colour | | | |
|-------------------------------|-----------------------------------------------------------------|--|--|
| orange brown with dark shades | | | |
| Format | | | |
| Moulding method | Hand form | | |
| DF: 214 x 101 x 65 mm | Between batches the average size and color may slightly differ. | | |

| Essential Characteristics - EN771-1 | | | | |
|---------------------------------------------|-------------------------|-------------------------|--|--|
| EN 771-1 - CPR-97884 NOBC 0063 (ex 0620) | O C | EN 771 - 1855-CPR-24914 | | |
| 2+ | | 2+ | | |
| Dimensional tolerances | T2 | | | |
| Range | R1 | | | |
| Active Soluble Salts | S2 | | | |
| Mean Compressive strength | >= 20 N/mm ² | Tested to the bed face | | |
| Normalized Compressive strength | NPD | Tested to the bed face | | |
| Dimensional stability | NPD | | | |
| Bond Strength general | 0,15 N/mm ² | | | |
| Bond Strength thin layer | 0,30 N/mm ² | | | |
| Reaction to fire | A1 | Category | | |
| Water absorption | <= 15% m/md | | | |
| Water vapour permeability | 5/10 | | | |
| Net dry density | 1690 kg/m³ (D1) | | | |
| Gross dry density | 1580 kg/m³ (D1) | | | |
| Thermal conductivity Lambda 50/50 | <=0,60 W/m.K | | | |
| Durability against freeze thaw | F2 | EN 772-22 | | |
| Dangerous substances | NL-BSB | According to Annex ZA 3 | | |

| Other Characteristics | | | | |
|------------------------------------------------------|---------------------|--------------------------------------|--|--|
| Initial rate of water absorption - Non-coated Bricks | 1,5 - 4.0 kg/m².min | Value according EN771-1:2011 - 5.3.8 | | |
| | (IW3) | Value according EN7/1-1.2011 - 5.5.8 | | |
| Initial rate of water absorption - Coated bricks | 0,5 - 1,5 kg/m².min | Value according FN771 1:2011 F 2.9 | | |
| | (IW2) | Value according EN771-1:2011 - 5.3.8 | | |
| Freeze/thaw resistance - PTV 23-002 | NPD | NBN 27-009 | | |
| Thermal conductivity Lambda 90/90 | 0,65 W/m.K | | | |
| Thermal conductivity Lambda Ui | 0,697 W/m.K | | | |
| Thermal conductivity Lambda Ue | 1,376 W/m.K | | | |











| Storage | & | hand | liı |
|---------|---|------|-----|
| | | | |

- Store packs on a clean surface and cover them
- Process from multiple packs at the same time
- Follow the Vandersanden processing guidelines

Cutting

Dry Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a

hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).

* All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.